

Express Mail No.: EL622260485US

Date of Deposit: 09/28/2001

APPLICATION FOR UNITED STATES LETTERS PATENT
FOR
HIGH-VELOCITY FORMING OF LOCAL FEATURES
USING A PROJECTILE

Inventor: Glenn S. Daehn

Attorneys: **STANDLEY & GILCREST LLP**
Attention: Roger A. Gilcrest
495 Metro Place South, Suite 210
Dublin, Ohio 43017-5319
Telephone: (614) 792-5555
Facsimile: (614) 792-5536
E-Mail: rgilcrest@standleyandgilcrest.com

09965993-092801
T08260-EL66591650

HIGH VELOCITY FORMING OF LOCAL FEATURES USING A PROJECTILE

Inventor: Glenn S. Daehn

BACKGROUND OF THE INVENTION

1. Field of the Invention

[0001] The present invention is directed to a system and method for the forming of local features in, and/or accomplishing the localized joining of sheet materials of various composition, by the contacting of the materials with a high-velocity projectile. The system and method The area of the sheet material to be formed is placed over a forming die having a cavity of desired shape. A preferably deformable projectile is then propelled into the area of the sheet material to be formed, such that a portion of the material is driven into the forming die. The system and method of the present invention may be used to form particular features in the sheet material, to join two or more sheets of material, or to connect a sheet of material to a secondary component,. When more than one material is used, the materials may be of like composition or, alternatively, the system and method of the present invention may be employed to join dissimilar materials.

2. Background

[0002] Many products are manufactured from metallic or other sheet materials, wherein the products require the forming of particular, localized features at certain locations thereon. Similarly, there are many products whose manufacture requires the attachment of one or more secondary components to a sheet material at one or several localized sites. In a typical attachment process, a secondary component may be locally joined to a sheet material by forcing a portion of the material through an opening in the component and into a subjacent cavity, whereby the shape of a cavity into which the material is forced thereafter causes the material

component to the sheet material. While the punch and die method of feature forming and localized joining is likely the most common method in use, it is not without limitations and problems. This process is generally limited to high ductility materials, because the operation of the punch and die generates a high shear force and may also cause a significant thinning of the materials to which it is applied. Such a mechanical process also typically requires a large structure for supporting the materials to be formed or joined, as well as a large force generating device, such as the hydraulic press mentioned above, to drive the punch into the die. In mechanical joining processes, the materials are also limited to joining by interlocking of the shapes produced by the punch and die, as a metallurgical bond between the materials cannot be developed thereby.

[0004] Electromagnetic forming has been used to generate high-velocity movement of a sheet, which can then be used to impart a shape to both entire metal sheets, and to smaller, localized features within a metal sheet. While electromagnetic forming has proven effective for use in forming large features, it is typically less effective when utilized to form smaller, localized features. The forming of localized features often requires the application of very high and localized forces. In such cases, process efficiency suffers, and small robust actuators are quite difficult to fabricate. Consequently, because it is very difficult to focus sufficient electromagnetic energy on a small surface area, it is generally not practical to use an electromagnetic forming process in this manner.

[0005] Localized high explosives have been used for some time to join primarily dissimilar metallic components. Typically, one component is situated at a slight distance from the other component, so that an explosive charge can be used to drive the components into contact with one another. The explosive charge causes

the components to collide at a sufficient velocity and angle to form a metallurgical bond therebetween. Explosive welding is commonly used to create sealed joints, such as vacuum joints, between metals such as aluminum, copper and stainless steel. Other uses for explosive welding may include the placement of a cladding onto a steel substrate, and the joining of aluminum to low-expansion metals in the electronics industry. Explosive welding is not typically used to form localized features or to join thin metallic sheets.

[0006] Ultrasonic or friction welding has also been used to join metallic and non-metallic components. Such methods involve placing the components into contact and causing movement along the joint interface located therebetween. Commonly, a friction weld is generated by rotating one component against a fixed second component under pressure. In this manner, sufficient frictional heat can be produced between the components such that at least one of the components can become plastic at the joint interface. When the rotational motion is halted, the components become physically bonded together. Friction welding also generally requires that at least one of the components be circular at the joint interface. Friction welding cannot be used to form localized features, and also cannot be used to join sheets of metallic materials in localized areas.

[0007] Hyper-pressure water jet pulses have recently been proposed to accomplish the bonding of aluminum components. In this method, a hyper-pressure pulse is developed by directing a high-pressure water jet pulse through a tapered nozzle to further increase its acceleration and pressure. Aluminum components to be joined are placed on an assembly fixture where they can be contacted with the hyper pressure water jet pulse. The hyper pressure water jet pulse can be used to cause a mechanical interlocking of the components and, if the stagnation pressure of

components to a sheet of material. The system and method of the present invention accomplishes these actions by contacting the sheet or sheets of material with a high-velocity projectile.

[0010] When used to form localized features, a sheet of material is preferably placed over a die containing a cavity, which cavity is of substantially the same shape as the desired localized feature to be formed. A projectile firing device is preferably located at some distance from the sheet of material and is substantially aligned with the die cavity. A preferably deformable projectile is then propelled from the projectile firing device into the sheet material, whereby the kinetic energy of the projectile forces a portion of the sheet of material into the die cavity – resulting in the formation of the localized feature.

[0011] When used to join two or more thin materials, the materials are similarly placed, preferably with substantially no gap therebetween, over a die containing a cavity. As in the forming method described above, the projectile firing device is used to fire a preferably deformable projectile into the materials where they overly the die cavity. Also as in the forming method, the materials are driven into the die cavity, wherein their shape is determined thereby. Using the system and method of the present invention, the materials may become joined by two mechanisms. First, the die cavity may be designed such that the materials will become mechanically interlocked with one another, such as is achieved in a traditional spot clinching process. Secondly, a metallurgical bond may be established between the materials as a result of the kinetic energy of the high-velocity projectile being transferred thereto. Thus, a stronger and more durable joint may be produced than may be accomplished by mechanical joining alone.

[0012] The projectile is preferably of a deformable material such as lead or plastic, but it is contemplated that other projectile materials may also be used, such as, for example, water in the form of liquid or ice. The projectile may be fired into the material(s) by any conventional means, such as, for example, by compressed air, explosive charge, electrical charge, or by any number of other means that are capable of accelerating the projectile to a sufficient velocity. The material(s) may be releasably secured in a position over the die cavity by clamping devices, by vacuum holding devices, or by means of a magnetic holding system.

[0013] Because the energy of the projectile can be effectively focused in a small region, the system and method of the present invention is especially useful for forming small and/or complex features, for achieving the localized joining of multiple sheets of material, in the attachment of secondary components to a sheet of material, or for joining a sheet material to a substantially more massive component. Also, it has been found through experimentation that the system and method of the present invention increases the forming limits of metallic sheet materials. More specifically, the system and method of the present invention appears to cause a through-thickness squeezing of the metallic material into the die cavity as opposed to causing a stretching of the material, thereby allowing the metallic sheet material to be thinned to a considerably greater degree without tearing than is typically possible by known forming systems and methods. Also, high-velocity deformation appears to actually inhibit the metal tearing process. Consequently, sharper, deeper, and more complex features may be formed without causing a tearing of the material, and lower ductility materials, which are typically stronger, may also be used. It has been found that the system and method of the present invention is also effective in minimizing or eliminating other problems associated with metal forming, such as, for example,

wrinkling and distortion. When used to join multiple sheets of material, the system and method of the present invention has been found to produce joints of increased strength, as the kinetic energy imparted to the materials by the high-velocity projectile is sufficient to produce an inertial welding of the materials that results in a metallurgical bond therebetween.

[0014] There are also aspects of the system and method of the present invention other than those already described above. For example, the equipment required to produce high-velocity forming or joining using a projectile is inexpensive in comparison to the equipment required to achieve similar results by the known, aforementioned techniques. No hydraulic or other press device is required as in the traditional punch and die technique, therefore there is no need for a large framework or for a complex, two-part, forming/joining die. Additionally, in the case of the system and method of the present invention wherein the materials are magnetically held in position above the die cavity, features and joints may be produced at arbitrary locations about large sheets of material, without the large clamping and support frame generally required by known techniques. Thus, the system and method of the present invention offers numerous advantages over known systems for producing localized features in sheet materials, for accomplishing the localized joining of multiple sheets of material, and for attaching secondary components to a sheet of material.

BRIEF DESCRIPTION OF THE DRAWINGS

[0015] In addition to the novel features and advantages mentioned above, other objects and advantages of the present invention will be readily apparent from the following descriptions of the drawings and exemplary embodiments, wherein like

reference numerals across the several views refer to identical or equivalent features, and wherein:

Figure 1 is a schematic view, in partial cross-section, depicting a typical punch and die process for forming a local feature in a sheet of material;

Figure 2 is a schematic view, in partial cross-section, illustrating a typical punch and die process for joining two sheets of material;

Figure 3 is a schematic view, in partial cross-section, representing one embodiment of the system of the present invention used to produce local features in a sheet of material;

Figure 4 is a schematic view, in partial cross-section, representing an embodiment of the system of the present invention used to produce a joint for locally joining multiple sheets of material;

Figures 5A and 5B are enlarged views illustrating the local feature and joint produced by the embodiments of the system and method of the present invention shown in Figure 3 and Figure 4, respectively;

Figure 6 is a schematic view, in partial cross-section, representing an alternate embodiment of the system of Figure 3, wherein a protective housing is utilized ;

Figure 7 is an enlarged isometric view of a feature formed in a steel sheet by impacting the steel sheet with a high-velocity projectile according to the system and method of the present invention;

Figure 8 is an enlarged cross-sectional view of the feature of Figure 7;

Figure 9 is an enlarged cross-sectional view of a joint formed between two sheets of metallic material by the system and method of the present invention; and

Figure 10 shows an alternate embodiment of the present invention, wherein one or more thin sheets of material may be joined to a substantially more massive component.

DETAILED DESCRIPTION OF THE EXEMPLARY EMBODIMENT(S)

[0016] As described above, the system and method of the present invention uses a high-velocity projectile to form local features in sheet materials, to join multiple sheets of material, to attach secondary components to a sheet of material, or to attach a sheet of material to a substantially more massive component. The system and method of the present invention is amenable to use with various materials, such as, for example, sheet metal. The joining process of the present invention may be used on either similar or dissimilar materials. The system and method of the present invention provides certain advantages over known systems and methods for accomplishing similar results. As stated previously, the most common of these known systems is likely the punch and die system. An example of a common punch and die system **10** that can be used for feature forming may be observed by reference to Figure 1. As can be seen, a sheet of material **15**, such as a piece of sheet metal, is placed between a punch **20** and a die **25** having a cavity **30** designed to impart a particular shape to the sheet of material. As indicated by the arrows, the punch **20** is adapted to contact the sheet of material **15** and to thereafter be withdrawn therefrom. Such a punch and die system is commonly installed into a hydraulic press, whereby the die is affixed to a stationary portion and the punch is affixed to a moving portion thereof. As the punch **20** is driven into the sheet of material **15**, the punch drives a portion of the sheet into the cavity **30** of the die **25**. The punch **20** is typically designed to enter only a certain depth into the cavity **30**.

into the die cavity **30**, which makes the material amenable to tearing. For this reason, features formed by this system and method must be of limited shape and sharpness, and the material used must generally be of high ductility. Similarly, the spot clinching process performed by the system **40** of Figures 2A-2B is inferior to the joining process that can be accomplished by the system and method of the present invention, because the spot clinch **70** relies only on the mechanical interlocking of the material sheets **45**, **50** for the strength of the joint. Additionally, as can be observed from Figure 2A and 2B, such a process is complex, and requires costly equipment to perform.

[0019] In contrast to the systems of Figures 1 and 2A-2B, as well as those described infra, the system and method of the present invention allows for the improved forming of local features, and for the creation of joints of increased strength via a metallurgical bonding of the sheets. An exemplary embodiment of a system **100** of the present invention designed for producing local features in sheet materials can be observed from the schematic representation thereof in Figure 3. A sheet of material **105**, in this particular embodiment a section of sheet metal, is arranged over a forming die **110**. The forming die **110** is preferably constructed of steel or another material with sufficient hardness to resist the impact of a high-velocity projectile **170** used to form the feature in the sheet of material **105**. The forming die **110** has a die cavity **115** that lies subjacent to the sheet of material **105** when the sheet of material is in contact with the forming die. The die cavity **115** is shaped to impart a particular feature **125** into the sheet of material **105**. In this particular embodiment of the present invention, the sheet of material **105** is releasably held in place along the surface of the forming die **110** by the vacuum of an evacuated chamber **120**. It should also be realized, however, that the sheet of material **105** could be

satisfactorily held in place by a clamping system, by magnetic attraction, or numerous other suitable means. Depending on the orientation of the forming die **110**, it is also possible that the sheet of material **105** may be formed without being releasably affixed in place above the forming die. However, affixing the sheet of material **105** during forming helps to ensure that the feature **125** will be formed in the correct location thereon.

[0020] An alternate embodiment of the present invention is shown in Figure 4. In this embodiment, the system **130** is designed to cause the localized joining of two sheets of material **135**, although it should be realized that more than two sheets of material may also be joined. In similar fashion to the system **100** of Figure 3, the sheets of material **135** are arranged over a forming die **140**. As in the previous embodiment, the forming die **140** is preferably constructed of steel or another material with sufficient hardness to resist the impact of the high-velocity projectile **170** (see Figures 3-4 and 6) used to join the sheets of material **135**. The forming die **140** has a die cavity **145** that lies subjacent to the sheets of material **130** when the sheets of material are in position over the die cavity. The die cavity **145** is preferably shaped either to produce an interlocking relationship between the two sheets of material **135** during the joining process, to cause the sheets of material to deform in a manner that promotes metallurgical bonding therebetween, or both. For example, the die cavity **145** may cause a portion of the sheets of material **135** to bulge outward, or may produce some other shape, such as a reentrant shape, that substantially prevents the extraction of the top sheet of material **150** from the bottom sheet of material **155** at the localized joint **175** (see Figure 5) formed by the joining process. The reentrant shape described herein and shown in the drawing figures is merely exemplary, however, and it should be realized that It is also possible to

0965993-092801
TOP SECRET

produce an interlocking joint between the sheets of material without requiring a reentrant shaped die cavity. The sheets of material **135** may be held in place during the joining process as described above or, alternatively, may be joined without being held in place. In this particular embodiment of the present invention, the sheets of material **135** are releasably held in place along the surface of the forming die **140** by the vacuum of an evacuated chamber **160**. It should also be realized, however, that the sheets of material **135** could also be held in place by a clamping system, by magnetic attraction, or numerous other suitable means.

[0021] Typical results of using the system and method of the present invention can be observed in more detail in Figures 5A-5B. Figure 5A shows an enlarged view of the die cavity **115** and surrounding portion of the die **110** of Figure 3, after the sheet of material **105** has been forced into the die cavity by the projectile **170**. As can be seen, a portion of the sheet of material **105** has been squeezed into the die cavity **115** and against the walls thereof, such that the shape of the die cavity is imparted to the sheet of material. It can also be observed in Figure 5A that the system and method of the present invention allows for a substantial thinning of the sheet of material **105** as it is forced into the die cavity **115** – without causing the material to tear. Similarly, Figure 5B illustrates an enlarged view of the die cavity **145** and surrounding portion of the die **140** of Figure 4, after the sheets of material **150**, **155** have been forced into the die cavity **145** by the projectile **170**. As can be seen, the projectile **170** forces a portion of each of the sheets of material **150**, **155** into the die cavity **145** to form an interlocking joint **175**. Although the joint **175** is shown to be of a reentrant shape in this particular example, interlocking joints of various shape may be formed. As in the feature of Figure 5A, a thinning of the sheets of material **150**, **155** may occur as a portion thereof is forced into the die

cavity **145**. A metallurgical bonding can be produced at points along the interface formed between the sheets of material **150**, **155** due to the transfer of kinetic energy from the projectile **170** thereto.

[0022] Another embodiment of the system of the present invention can be seen in Figure 6. In this particular embodiment, the system **200** is provided with a protective enclosure **205** that preferably encapsulates a portion of a projectile firing device **165** and the area between the projectile firing device and the portion of the sheet of material **210** that will be contacted with the projectile **170**. The protective enclosure **205** preferably helps to ensure that contact with the moving projectile **170** after its firing from the projectile firing device **165** is difficult, if not impossible. The protective enclosure **205** also preferably contains any projectiles that may ricochet after contact with the sheet of material **210**. A magnetic holding system, in this embodiment consisting of pairs of magnets **220**, **225**, is located in the protective enclosure **205** and a portion of a structure **230** to which the die **215** is mounted, respectively. The sheet of material **210** may be moved between a gap situated between the magnets **220**, **225** and into the area of the die **215** to reside over the die cavity **235**. It should also be understood that such a protective enclosure **205** could be used in conjunction with the evacuated chamber **120** system of Figure 3, or other sheet holding systems. Thus, in addition to increasing the safety of the system and method of the present invention, the protective enclosure **205** further provides an effective and inexpensive method of accomplishing the securing of the sheet of material **210** and the proper alignment of the projectile firing device **165** with the die cavity **235**.

[0023] In each of the embodiments illustrated in Figures 3-4 and 6, the projectile firing device **165** can be observed to be substantially aligned with the die

ft/sec is sufficient to accomplish either feature forming or localized joining. The proper velocity is, of course, dependent on, among other factors: the task to be performed; the type of material that will be contacted by the projectile; the thickness of the material in the area of impact; the specific geometry of the feature to be formed or the joint to be created; the composition of the projectile; the shape of the projectile; and the mass of the projectile.

[0025] The shape of the projectile **170**, as depicted in Figures 3-4 and 6 is shown to be substantially similar to the size and shape of the die cavity **115**, **145**, **235**. Providing a projectile of such a size and shape allows substantially the entire mass of the projectile to force the sheet of material into the die cavity. Accordingly, the size, shape and mass of the projectile may vary significantly depending on the size and shape of the feature to be formed in the sheet of material, as well as the composition of the sheet of material. The composition of the projectile may also vary. Preferably, the projectile is comprised of a deformable material, such that the projectile can substantially conform to the shape of the die cavity as it forces the sheet of material therein. For purposes of illustration, and not limitation, the projectile may be composed of a metallic material, such as lead, of a deformable plastic such as polyethylene, or of a liquid, such as water. Water in the form of ice may also be used as a projectile. As projectiles are fired into the sheet or sheets of material, the projectiles will typically become deformed. Preferably, a means is provided to collect the deformed projectiles. Depending on the operation performed by the projectile, the composition thereof, and the projectile firing device used, the projectile may be reused as recovered, may be recycled and reused, or may be discarded. In the case of a liquid projectile, in the form of ice or water, the projectile need merely be drained away from the die, or allowed to melt and drain away.

[0026] An example of a feature formed in a low-ductility steel sheet by the system and method of the present invention can be seen in Figures 7-8. It has been found that the system and method of the present invention is able to increase the forming limits of metal sheets, and can also effectively treat certain other metal forming problems, such as, for example, wrinkling and distortion. This appears to be primarily due to the high velocity of the projectile used to form the feature in the metal sheet being able to suppress fracturing of the metal during formation of the feature. The fracturing is suppressed largely because the projectile causes a through-thickness squeezing of the metal into the cavity, rather than a stretching of the metal as is produced by the traditional punch and die method. As such, the metal forced into the cavity may experience more thinning without tearing than is typically possible using known systems and methods. As a result of this phenomenon, lower ductility materials may be formed into features having geometries not traditionally possible. The feature of Figures 7-8 is exemplary of this aspect of the present invention. The feature of Figures 7-8 was formed in a low-ductility steel which normally allows for less than a 5% elongation before failure, such as tearing. However, as can be best observed by reference to Figure 8, employing the system and method of the present invention permits the feature illustrated therein to be produced with a material thinning in excess of 30% - without failure.

[0027] An example of the localized joining of multiple sheets that may be accomplished by the system and method of the present invention is illustrated by the joint of Figure 9. The joint of Figure 9 was formed, substantially as depicted in Figure 4, by placing the two metallic sheets over a cavity in a forming die, and firing a projectile into the metal sheets. The projectile squeezes the sheet metal into the

die cavity, where the sheet metal is formed thereby. Preferably, the die cavity is shaped to form an interlocking joint between the metal sheets, such that the sheets cannot be readily separated after the joint is formed. While such an interlocking joint may be sufficient to secure the sheets together, the present invention also allows for a further bonding between the sheets to be achieved. In the joint of Figure 9, for example, the velocity and resulting kinetic energy of the projectile was sufficient to cause an inertial welding between the metal sheets. More specifically, the inertial welding was accomplished by the transfer of kinetic energy from the projectile to the sheet metal during impact. As the sheet metal was forced into the die cavity by this kinetic energy, certain portions of the metal were transformed into a plastic state by the pressure on the metals and the sliding friction that occurred between the two sheets. As the transfer of kinetic energy occurs extremely quickly during this process, the plastic deformation and subsequent cooling also occurs very quickly. Due to the frictional work breaking up surface oxides and allowing intimate contact, a metallurgical bond is established between the sheets that creates or further strengthens the formed joint.

[0028] As illustrated in Figure 10, the system and method of the present invention can also be employed to join a relatively thin sheet(s) of material **255** to a substantially more massive component **260**. In this embodiment **250** of the present invention, a die may not be necessary. As can be seen, a receiving shape **265** may be cut or otherwise formed in the more massive component **260** at the desired joining location. The sheet(s) of material **255** may then be placed in position over the more massive component **260** and preferably secured in place by any of the securing means previously described. If the more massive component **260** is of sufficient mass, a projectile **170** may then be fired from a projectile firing device **165**

into the sheet(s) of material **255**, with the more massive component itself resisting the force of the projectile. The impact of the projectile **170** forces a portion of the sheet(s) of material **255** into the receiving shape **265**. As shown in the drawing figures and described infra, the receiving shape **265**, like the die cavity **145**, **235**, may be designed to produce a mechanical interlocking between the more massive component **260** and the sheet(s) of material **255**. Although the receiving shape **265** in this particular embodiment is shown to have a reentrant shape, it should be realized that such a shape is not essential to producing an interlocking joint. The receiving shape **265** may also be designed to encourage the formation of a metallurgical bond between the more massive component **260** and the sheet(s) of material **255**. Thus, joining of the more massive component **260** and the sheet(s) of material **255** may be accomplished by either of these techniques, or by a combination of both.

[0029] While not specifically shown in the drawing figures, it is also possible to use the system and method of the present invention to join or attach secondary components to a sheet of material, as well as, or rather than to accomplish the joining of two sheets. For example, a component adapted to be joined to a sheet of material may be placed into a die cavity, which cavity may be similar to those depicted in the drawing figures. The component preferably has an aperture or other structure for receiving a portion of the sheet of material that has been located over the die cavity. The projectile may then be fired into the sheet of material to force a portion thereof through the aperture in the component. The die is preferably designed to cause the material being forced through the aperture to bulge outward as it passes therethrough. The material is then forced to expand to a point beyond the circumference of the aperture, thereby causing the component to become

attached to the sheet of material. Such a method may be used, for example, to install a tab to the top of a beverage can.

[0030] It can be realized from the foregoing, that the system and method of the present invention allows for a novel forming and joining of thin or sheet materials. While certain embodiments of the system and method of the present invention have been described above and in the accompanying drawing figures, it should be realized that modifications may be made thereto. For example, there can be a multitude of projectile shapes and compositions used. Numerous different materials may be formed or joined, as well multiple layers of material, and materials of various thickness. It should also be realized that the present invention is not limited to use with metallic materials, as any material having suitable ductility may be formed or joined. The projectile may also be fired into the sheet material by numerous means, as recited infra. Therefore, the scope of the invention is not to be considered limited by the foregoing disclosure, and modifications are possible without departing from the spirit of the invention as evidenced by the following claims:

09965993-092801